



3M™ Safety-Walk™ 610

General Purpose Anti-slip Adhesive Tape

Product Bulletin

Product Description 3M™ Safety-Walk™ 610 consists of abrasive particles bonded by a sustainable tough, durable polymer to a dimensionally stable plastic film. The reverse side is coated with a rubber based pressure sensitive adhesive, covered by a removable protective liner. As part of implemented sustainability improvement on this product by water-based manufacturing process, the product provides an improved durable, slip resistant surface for a large variety of applications.

Primarily for use as a durable, slip resistant surface for dry, wet, oily floors in industrial and commercial applications with intensive pedestrian or light vehicle traffic such as: corridors, production and storage rooms, ramps, stairways, ladders, footplates on machines, emergency exits.

Product Features

- Improved sustainability (environmental benefit)
- Certified as phthalate-free
- Improved safe, slip resistant surface
- Improved high durability
- Improved weathering
- More resistant to chemicals
- UV resistant
- Easy to install by higher flexibility at cold weather performance
- Excellent bond to most dry, clean, smooth surfaces

Sizes The Safety-Walk General Purpose Tapes are available in different roll width and in different pre-cut treads. Please contact your local 3M contact for further information.

Accessories 3M primers (non exhaustive list):

- 3M™ Tape Primer 83
- 3M™ Primer 94
- 3M™ Edge Sealing Compound 1103

Hand roller

Product Characteristics These are typical values. Please contact your 3M representative for a custom specification.

Physical & Application	Property and Test Method	Value / Result
	Applied thickness	0.71 mm
	Applied weight	732 g/m ²
	Resistance to UV	Good
	Fire behaviour	
	EN 13501-1: 2010	Bfl s1
	FAR 25 853 Appendix F, Part 1	
	Section (a)(1)(ii)	Passed
	Section (a)(2)(ii)	Passed
	EN45545-2: 2016 R10	HL1/HL2
	EN ISO 5658-2: 2006	CFE (kW/m ²) = 20; Qsb (MJ/m ²) = 3.1
	UNI CEI 11170: 2007 EN ISO 11925-2:2010	Passed
	IMO FTP Code Resolution MSC 61 (67)	
	- Annex 1: Fire test procedures	Passed
	- Part 2: Smoke and toxicity test	Passed

Smoke Density (Dm corrected):**ASTM E662-09**

- Flaming	98
- Non-flaming	97

Property and Test Method**Value / Result****Static coefficient of friction: MIL-C-24667 (SH)**

Surface	Condition	Minimum	Values
Rubber	Dry	0.60	1.40
	Wet	0.60	1.30
	Oil	0.60	1.17
Leather	Dry	0.60	1.00
	Wet	0.60	1.64
	Oil	N/A	N/A

Dynamic coefficient of friction: MIL-C-24667 (SH)

Surface	Condition	Minimum	Values
Rubber	Dry	0.50	1.04
	Wet	0.60	1.01
	Oil	0.30	0.87
Leather	Dry	0.40	0.74
	Wet	0.40	1.19
	Oil	N/A	N/A

Slip Resistance: DIN 51130: 10.2010

Slip Resistance R = 13

Displacement volume V = 4

Minimum Application Temperature +4°C / 40°F

Service Temperature -40°C (-40°F) / +79°C (+175°F)

Chemical Resistance	Water	R
	Soap (1% Ivory Flakes in water)	R
	Detergent (1% Dreft in water)	R
	Bleach (5.25% sodium Hypochlorite)	R
	1% Sodium Hydroxide	R
	1% Hydrochloric Acid	R
	25% Sulfuric acid in water	R
	Isopropyl Alcohol	R
	Methyl Ethyl Ketone	I
	Mineral Spirits	NR
	Trichloroethylene	NR
	Peanut Oil	R
	Hydraulic Fluid (Skydrol 500B)	R
	Motor Oil	R
	Gasoline (unleaded)	IC
	Diesel fuel	I
	50% Anti-freeze in water	R
	Wind screen washer fluid	R

R = Recommended for non continuous immersion

I = Recommended for intermittent exposure only

NR = Not recommended

IC = Can stand incidental contact, if thorough weekly cleaning/rinsing

Note: The recommendations noted here are based on results of 7-day immersion tests bonded to stainless steel.

Storage	Shelf life	5 years from the date on the original box
	Storage conditions!	+15°C to +30°C, out of sunlight, original container in clean area, humidity: 50% - 60%.
Disposal	Post-consumer waste can be disposed of in appropriate containers and/or be incinerated. European code for waste disposal: 20.01.04	
Origin	Made in USA with globally sourced materials	

Durability When exposed to pedestrian traffic only, the product will stand at least 1 million crossings (approx. 3 years if 1,000 people walking over every day).
Wheeled traffic will significantly reduce product life.

Surface Preparation Make sure surface is clean, dry, smooth and above minimum temperature of application.
Repair or replace any damaged or broken surface.
Remove chipped, cracked or peeled paint from surface.
Strip waxed floors prior to washing.
Use appropriate cleaner or solvent wipe to clean surface:

Type of Surface	Recommended preparation
-----------------	-------------------------

Bare metal, polyethylene, polypropylene	Solvent wipe
---	--------------

Painted metal, painted plastics, painted wood, gel-coated fiberglass, epoxy floors	Solvent wipe or degrease wash, rinse and let dry
--	--

Porous concrete	Degrease wash, rinse and let dry
-----------------	----------------------------------

Painted concrete	Degrease wash, rinse and let dry
------------------	----------------------------------

Vinyl tile, marble, terrazzo, ceramic	Strip off floor finish, wash, rinse and let dry
---------------------------------------	---

Quarry tile	Degrease wash, rinse and let dry
-------------	----------------------------------

Application Tools needed:
rubber hand roller or rubber mallet

1. Individual pieces should be spaced a minimum of 12 mm apart and a maximum of 50 mm apart.
2. Round the corners of any pieces cut from rolls.
3. Peel protective liner back about 50 mm from one end and position piece on surface.
Note: minimize touching (contaminating) adhesive with fingers.
4. Continue to remove liner and press firmly in place as liner is removed.
5. For small pieces, peel liner off piece. Holding piece by its edges, curve it gently with the adhesive side out. Align the middle of the piece over the middle of the target surface and press down.
6. Finally press into firm contact with surface using a rubber hand roller by starting in middle and rolling out towards edges.
7. On steps, apply 3M Safety-Walk materials 12 to 15 mm from stair edge to prevent edge curl and premature wear.

Helpful hints for proper application **Rough or smooth, porous surfaces:**
Prime coat with a 3M primer is recommended for proper adhesion.

Painted surfaces:

3M Safety-Walk materials can be applied on most painted surfaces which are in good condition and will adhere as well as the base paint. Painted surfaces must be thoroughly dry before the application.

Treated and untreated wood:

Wood surfaces must be sealed or painted before application of 3M Safety-Walk materials.

Immersed surfaces:

Do not apply 3M Safety-Walk materials on surfaces with constant water contact or moisture seepage.

Grouted floors:

Do not bridge over grouting, cracks or breaks in all surfaces. Cut into smaller pieces.

Kitchen and greasy floors:

Application of 3M Safety-Walk materials is not recommended for quarry tile in commercial kitchens.

Wet areas:

For extra protection from excessive moisture or liquids (not constant moisture) use 3M Edge Sealer to protect the edges of 3M Safety-Walk materials against penetration of liquids.

Priming

1. Properly clean the floor following "surface preparation" procedure.
2. Use a paint brush and paint on a thin coat of primer where the 3M Safety-Walk materials are to be applied.
3. Allow the primed area to dry thoroughly (no evidence of stickiness or tackiness) before applying 3M Safety-Walk material.

Note: Primers are not recommended with the clear grade because the transparency benefit is then lost.

Maintenance

Periodically inspect product application to maintain product effectiveness.

Keep free of dirt and other residue that might impair functionality.

General purpose treads should be decked-brushed regularly.

Use appropriate degreaser/cleaner as a general maintenance cleaner to keep material and surrounding surfaces free of soil and grease.

Removal and Replacement

To remove and replace worn or torn material:

Start by pulling up old material. Use of a heat gun and a scraper will assist in this process.

After total removal of old materials, use a degreaser or solvent based cleaner to remove adhesive residues before proceeding with re-application of 3M Safety-Walk materials.

Remarks

This bulletin provides technical information only.

Important notice

All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.

Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.

Additional Information

Visit the web site of your local subsidiary at www.3M.eu/facilities for getting:

- a complete product overview about materials 3M is offering

Commercial Solutions Division

Hermeslaan 7
1831 Diegem, Belgium

Responsible for this technical bulletin

3M Deutschland GmbH | Safety & Graphics Laboratory
Carl-Schurz-Str. 1 | 41453 Neuss, Germany

3M and Safety-Walk are trademarks of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.