



Specifications

Standard Document Requirements of:
ANSI/ESD S20.20 and ANSI/ESD S541

Meets
Packaging

Electrical Properties **Typical Values**
Rs Resistance: 1 x 10⁹ to < 1 x 10¹¹ ohms

Test Procedures/Method
ANSI/ESD STM11.11

Physical Properties

Construction: Cellulose film tape coated with a high tack, non-staining, rubber adhesive system on plastic core
Thickness: 1.9 mil 0.0019", (0.06 mm)
Color:* Clear, with ESD Symbols
Temperature Range: -10°C to +71°C (+14°F -to +160°F) 100°C for 10 min max

Sulfur Content: No Sulfur
Backing: Cellulose
Adhesive: Synthetic Rubber
Tensile: 22 LBS./IN
Adhesion: 59 OZ/IN
Elongation: 22.5%

Tape	0.5"	0.75"	1"	2"	Core	Length
Clear	46900	46901	46902		1"	36 yds
	46903	46904	46905	46906	3"	72 yds
Clear with Symbols	46909	46910	46911	46912	3"	72 yds
Clear w/ Symbols and Yellow Stripe	46913	46914	46915	46916	3"	72 yds

Width tolerance ±1/32"

Tape widths are nominal metric ±0.8 mm (±1/32")

1/4" is 6 mm nominal or 0.236"
1/2" is 12 mm nominal or 0.472"
3/4" is 18 mm nominal or 0.709"
1" is 24 mm nominal or 0.945"
2" is 48 mm nominal or 1.890"

*Military organizations sometimes use MIL-STD-1285 for hardware marking and that document once required the use of the "three arrows in a circle" symbol. That symbol has been changed for consistency with industry marking to the "hand in triangle" ESD Susceptibility symbol."
(Ref: ESD TR20.20 section 5.3.14.1)

Specifications and procedures subject to change without notice

RoHS 3, REACH, and Conflict Minerals Statement

See the Desco Industries RoHS 3, REACH, and Conflict Minerals Statement:
www.descoindustries.com/ROHS.aspx

See the Protektive Pak Limited Warranty:
ProtektivePak.DescoIndustries.com/Limited-Warranty.aspx

See the Protektive Pak Disclaimer:
ProtektivePak.DescoIndustries.com/Disclaimer.aspx

No sulfur, surfactants, amines, or silicone based material (adhesive, film backing, release material) is used in the manufacture of our cellulose tape.

Wescorp Tape Storage and Limited Warranty:

The user must determine the suitability for use of an ESD tape for his particular application. For best results, tape inventory should be continually replenished. It is recommended that rolls of tape be stored flat and rotated (flipped over to the other side) periodically. Tapes should be stored in a dry, well ventilated room with a reasonably consistent temperature of 68°F (20°C) and be protected from exposure to direct sunlight. Tape should not be stored in ultraviolet sunlight, moisture, or heat. Tape over one year old should be evaluated by the user to determine acceptability for the user's application. Desco Industries, Inc. recommends those tracking useful life of product to use shipping/invoice date as Desco Industries, Inc. expressly warrants that for a period of one (1) year from the date of purchase, our Wescorp Brand ESDTape will be free of defects in material (parts) and workmanship (labor). See details of Limited Warranty online at ProtektivePak.com/Warranty.aspx

*Wescorp is a Desco Industries, Inc. brand.

Note: Tape rolls may vary slightly in color.

WESCORP* ANTISTATIC CELLULOSE TAPE

PROTEKTIVE PAK

PROTEKTIVE PAK
13520 MONTE VISTA AVENUE, CHINO, CA 91710
PHONE: (909) 627-2578 FAX: (909) 363-7331
WEBSITE: www.ProtektivePak.com

DRAWING NUMBER:
46900

DATE:
July
2017

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Protektive Pak:

[46911](#) [46912](#) [46900](#) [46901](#) [46902](#) [46903](#) [46904](#) [46905](#) [46916](#) [46906](#) [46909](#) [46910](#) [46913](#) [46914](#) [46915](#)