

CCRG Conformal Coating Remover Gel

CCRG is a thixotropic gel formulated to remove solvent resistant conformal coatings, including Electrolube DCA, DCAFD, DCB, DCR, DCRT, DCE, PUC, PUCAF and WBP/S. This product does not contain methylene chloride.

Approvals	RoHS-2 Compliant (2011/65/EU):	Yes
Liquid Properties	Appearance:	Colourless Gel
	Density @ 20°C (g/ml):	0.950 g/ml
	VOC Content:	98%
	Flash Point:	-17°C CC (Closed cup)

<u>Description</u>	<u>Packaging</u>	<u>Order Code</u>	<u>Shelf Life</u>
<u>Conformal Coating Remover Gel</u>	1 Litre	CCRG01L	36 Months

Directions for Use

Areas where the conformal coating is to be removed should be identified. CCRG should be applied in small sections using a brush or syringe. CCRG will then start to attack the coating lifting it from the surface, after which the gel should be wiped off or promptly rinsed off with deionised water – do not allow the gel to fully dry out.

This method should be repeated until the required area is clean.

CCRG will not generally damage metals; however, there may be some corrosion on ferrous metals if materials are soaked for prolonged periods. CCRG will attack several plastics and also remove component identification markings if prolonged exposure is permitted. Where possible, a compatibility test with sensitive plastics should be conducted prior to full-scale use.

A removal solvent (RRS) is also supplied, should a liquid product be required. CCRG is highly flammable so care must be taken when using this material. Refer to the Material Safety Data Sheet for additional information.

Revision 1: Oct 2013