

Note: Tolerances are ±.38mm (.015") unless otherwise specified.


| Part<br>No.  | RoHS                | PCN | lFiaure | Case<br>Style | l A | В                | С | D               | E   | F              | Thickness                  |
|--------------|---------------------|-----|---------|---------------|-----|------------------|---|-----------------|-----|----------------|----------------------------|
| 56-02<br>-95 | RoHS ✓<br>Compliant | N/A | 1       |               |     | 18.80<br>(0.740) |   | 6.98<br>(0.275) | N/A | 5.59<br>(.220) | 0.05/0.10<br>(0.002/0.004) |

| 56-02<br>-<br>101G* | RoHS √<br>Compliant | N/A                         | 2 | TO-<br>218 | 26.16<br>(1.000) | 22.61<br>(0.890) | 17.91<br>(0.705) | 8.26<br>(0.325) | N/A             | 11.30<br>(.144) | 0.05/0.10<br>(0.002/0.004) |
|---------------------|---------------------|-----------------------------|---|------------|------------------|------------------|------------------|-----------------|-----------------|-----------------|----------------------------|
| 56-77<br>-10        | RoHS √<br>Compliant | N/A                         | 3 | TO-<br>220 | 21.89<br>(0.862) | 13.21<br>(0.520) | 14.73<br>(0.580) | 5.26<br>(0.270) | 5.08<br>(0.200) | 1.75<br>(0.070) | 0.05/0.10<br>(0.002/0.004) |
| 56-77<br>-8G        | RoHS √<br>Compliant | Product<br>Change<br>Notice | 2 | TO-<br>220 | 18.93<br>(0.745) | 13.84<br>(0.545) | 13.54<br>(0.533) | 5.38<br>(0.212) | N/A             | 3.81<br>(0.150) | 0.05/0.10<br>(0.002/.004)  |
| 56-77<br>-11G       | RoHS √<br>Compliant | Product<br>Change<br>Notice | 2 | TO-<br>220 | 18.93<br>(0.745) | 13.84<br>(0.545) | 13.54<br>(0.533) | 5.38<br>(0.212) | N/A             | 3.05<br>(0.120) | 0.05/0.10<br>(0.002/0.004) |
| 56-03<br>-2G        | RoHS √<br>Compliant | Product<br>Change<br>Notice | 4 | TO-3       | 42.04<br>(1.655) | 27.00<br>(1.063) | 3.96<br>(0.156)  | 1.57<br>(0.062) | N/A             | N/A             | 0.05/0.10<br>(0.002/0.004) |
| 56-03<br>-8G        | RoHS √<br>Compliant | Product<br>Change<br>Notice | 4 | TO-3       | 42.85<br>(1.687) | 30.15<br>(1.187) | 3.96<br>(0.156)  | 1.57<br>(0.062) | N/A             | N/A             | 0.05/0.10<br>(0.002/0.004) |

<sup>\*</sup> This insulator is also for TO-18, TO-247, and TO3P.

Note: Tolerances are  $\pm .38$ mm (.015") unless otherwise specified.

| Property   | Typical Value 25℃                      |  |  |  |  |  |  |
|--|--|--|--|--|--|--|--|
| Electrica  |  |  |  |  |  |  |  |
| Dielectric Strength 0.025mm to 0.076mm thick in air (1 to 3 mils thick in air) | 172 x 103 volts/mm (4500 volts/mil     |  |  |  |  |  |  |
| Dielectric Constant  | 6.5 to 8.7                             |  |  |  |  |  |  |
| Dissipation Factor 106 Cycles  | .0001004                               |  |  |  |  |  |  |
| Volume Resistivity   | 1015 ohm-cm                            |  |  |  |  |  |  |
| Physical   |  |  |  |  |  |  |  |
| Modulus of Elasticity in Tension   | 172 x 103 (25 x 106 psi)               |  |  |  |  |  |  |
| Tensile Strength   | 310 MPa (45,000 psi)                   |  |  |  |  |  |  |
| Hardness Mohs  | 3.0                                    |  |  |  |  |  |  |
| Shore  | 115                                    |  |  |  |  |  |  |
| Comprehensive Strength   | 2.21 x 108 Pa (32,000 psi)             |  |  |  |  |  |  |
| Specific Gravity   | 2.9                                    |  |  |  |  |  |  |
| Thermal  |  |  |  |  |  |  |  |
| Thermal Conductivity:  | 0.528 Wm-1 °C-1<br>(0.30 Btu/hr.ft °F) |  |  |  |  |  |  |
| Coefficient of Thermal Expansion   | 3.24 x 10-5/℃<br>(1.8x 10-5/℉)         |  |  |  |  |  |  |
| Specific Heat  | .084 KJ/Kg℃<br>(.02 Btu/Lb ℉]          |  |  |  |  |  |  |
| Melting Point  | 1275℃                                  |  |  |  |  |  |  |
| Maximum Operating Temperature (1022℃)  | 550℃                                   |  |  |  |  |  |  |
| Chemical Composition   |  |  |  |  |  |  |  |
| Silica   | 45.4%                                  |  |  |  |  |  |  |
| Alumina  | 37.5%                                  |  |  |  |  |  |  |
| Potash   | 12.0%                                  |  |  |  |  |  |  |
| Water  | 5.0%                                   |  |  |  |  |  |  |



| Part<br>Number         | ID              | OD               | Diameter<br>Tolerances | Thickness                  |  |
|------------------------|-----------------|------------------|------------------------|----------------------------|--|
| 56-02-10G 5.16 (0.203) |                 | 14.30<br>(0.563) | ±13 (0.005)            | 0.05/0.10<br>(0.002/0.004) |  |
| 56-02-72G              | 6.55<br>(0.258) | 25.40 (1.00)     | ±38 (0.015)            | 0.10/0.15<br>(0.004/0.006) |  |

## **Customer Assistance**

Contact Us
Get Design Assistance
Find a Distributor
Find a Sales Rep
Request a Quote
Placing an Order
Terms and Conditions
Returns

## **Popular Products**

Extrusions Board Level Liquid Cooling Heat Pipe Technology Heat Sink Accessories Interface Materials

## Our Company

About Aavid
News and Events
Management Team
Worldwide Locations
Directions to Headquarters
Disclaimer
Customer Survey
Privacy Policy

Sign up to receive Aavid news & alerts





Aavid will lead the electronics thermal management industry worldwide. We will be the first company customers call to enable their thermal designs anywhere in the world. We will respond with extraordinary speed and will provide them with timely and cost-effective solutions because we understand their needs, their industry, and their culture. 2012 Aavid Thermalloy, LLC

## **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Aavid:

56-77-8G 56-02-95G